

Optical response of a ferromagnetic/DMS hybrid structure

P. Redliński,* T. G. Rappoport, A. Libal, J. K. Furdyna, and B. Jankó
Department of Physics, University of Notre Dame, Notre Dame, IN 46556

T. Wojtowicz
*Department of Physics, University of Notre Dame, Notre Dame, IN 46556 and
 Institute of Physics, Polish Academy of Sciences, Warsaw, Poland
 (Dated: February 2, 2008)*

We investigate the possibility of using local magnetic fields to produce one-dimensional traps in hybrid structures for any quasiparticle possessing spin degree of freedom. We consider a system composed of a diluted magnetic semiconductor quantum well buried below a micron-sized ferromagnetic island. Localized magnetic field is produced by a rectangular ferromagnet in close proximity of a single domain phase. We make quantitative predictions for the optical response of the system as a function of distance between the micromagnet and the quantum well, electronic g -factor, and thickness of the micromagnet.

The use of the spin of quasi-particles, instead of their charge, as a basis for the operation of a new type of electronic devices has attracted the attention of a large interdisciplinary research community. The interest is not only in the phenomenology but also in the large scale production and applicability of such devices [1]. In this paper we show that the spin degree of freedom can be utilized for achieving spatial localization of charged quasi-particles such as electrons, holes or trions [2, 3], as well as of neutral complexes such as excitons [4, 5]. This is of interest for spintronic applications. In diluted magnetic semiconductors (DMS) like CdMnTe, due to the exchange interaction between delocalized band electrons and localized magnetic ions, the presence of a static magnetic field leads to a giant Zeeman splitting between band states for different spin components. As a consequence, the effective g -factor for the DMS is very high and temperature dependent [6, 7].

Here we consider a hybrid structure of a CdMnTe/CdMgTe quantum well (QW) at tens of nanometers below a rectangular ferromagnetic island. We find that due to the giant Zeeman interaction, the non-homogeneous magnetic field produced by the rectangular ferromagnetic island acts as an effective potential that can efficiently “trap” spin polarized quasi-particles in the QW. We present quantitative predictions for the optical response of the DMS where the localization of the quasi-particles is evident. We also discuss how these predictions are sensitive to the variation of certain parameters, such as the distance between the QW and the ferromagnetic island, the thickness of the micromagnet, and the electronic g -factors (g_e - g -factor of the electron, g_h - g -factor of the hole).

We consider a typical rectangular micromagnet (iron) of dimensions $D_x=6\text{ }\mu\text{m}$, $D_y=2\text{ }\mu\text{m}$ and $D_z=0.15\text{ }\mu\text{m}$ in a single domain state [8], with magnetization pointing in the x -direction [9, 10, 11], see Fig. 1. The single

domain state of the micromagnet was investigated with micro-magnetic simulation using the OOMMF package made available by NIST [12]. In the absence of an external magnetic field the micromagnet has a multi-domain structure. The simulation shows that after magnetizing the sample with a field of 1 T and then reducing the field to 0 T, a value of 0.2 T is enough to restore a state that is, for our purposes, sufficiently close to a single domain. Because of the magnetic anisotropy of the g_h -factor, this additional field is unimportant for an electron in the valence band but can slightly affect electrons in the conduction band.

Due to the spatial variation of the local magnetic field (Fig. 1) [9, 11] and to the presence of the QW, the quasi-particles are localized below the poles of the micromagnet [9]. Localization occurs only in two spatial dimensions (x and z), while the quasi-particles can move quasi-freely in the third (y) direction. As we will show later, the spin traps and optical response of the quasi-particles are very sensitive to the value of electron and hole g -factors. In most of our calculations we use an electron g -factor $g_e=500$ obtained experimentally and reported by Dietl *et al.* [13]. Assuming that in CdTe structures the ratio of exchange interactions $|\beta/\alpha| = 4$, we obtain $g_h=2000$.

In Fig. 1 we present a sketch of the energy levels of the QW for two cases: first, with no ferromagnetic island present; and second, in the presence of a ferromagnetic island on top of the QW. With no ferromagnetic island, the main absorption edge (MAE) in the σ_+ polarization of light is observed between the states of the heavy hole HH_1 with spin $-3/2$ and the electron E_1 with spin $-1/2$. Due to the absence of magnetic field, E_1 and HH_1 are two-fold degenerate with respect to the direction of the pseudo-spins; and the first optical transition in σ_- polarization is at the same energy as the σ_+ transition. After depositing the micromagnet, we expect new states to appear below E_1 and above HH_1 . As indicated in Fig. 1, depending on the parameters, some of the states can be even inside the QW gap. Note that the edges of the conduction as well as the valence bands are plotted for the quantum structure without the effect of the island. The

*Electronic address: Pawel.Redlinski.1@nd.edu




FIG. 1: Top: z -component of the magnetic field at distance d below magnetic island. The micromagnet is magnetized in the x -direction. Bottom: with no magnetic island present, we expect the main absorption edge (MAE) to be between HH_1 and E_1 states shown by the solid lines. Conduction as well as valence band edges are plotted for a QW structure without any additional magnetic field; After the deposition of the island new states appear below E_1 and above HH_1 (dashed lines), and each energy state is *non-degenerate*. For additional explanation see text.

new states are non-degenerate, since the presence of a local magnetic field lifts the Kramers degeneracy. Below E_1 we have only conduction electron states of spin $-1/2$; and above HH_1 , states are built up mainly from valence electrons with pseudo-spin $-3/2$. Transitions between these new states appear in the absorption below the main absorption edge according to selection rules for the $\sigma_{\pm}$ polarizations, as shown in Fig. 2 [14]. The label (11) in Fig. 2 shows the lowest possible transition between valence and conduction band states.

For typical quasi-particle masses the motion of the conduction and valence electrons is quasi-free in the y -direction. Therefore we should rather speak about bands than individual levels. On the other hand we know that Coulomb interaction will create excitons which form sharp individual optical lines. Furthermore, it is assumed that exciton states are formed and the MAE corresponds now to the 1S exciton transition line in the QW without the island. In Fig. 2, Fig. 3 and Fig. 4 we take the zero energy at the 1S exciton main absorption peak.

In our calculations we model valence band electrons using a two-band Luttinger Hamiltonian [15, 16], and for the conduction band electrons we use a quadratic Hamiltonian. Including the Zeeman interaction, we diagonalize the total Hamiltonian and obtain one electron states of




FIG. 2: Absorption coefficient for three different distances d between the rectangular ferromagnetic island and the QW. The thickness of the micromagnet is $D_z=150$ nm, and $g_e=500$. The numbers (nm) correspond to transitions between the n th electron state and the m th hole state.

the valence and conduction bands, together with their corresponding wave functions. Using these states and wave functions, we then calculate the oscillator strengths of the optical transitions as well as the optical absorption coefficients for the σ_+ polarization [14].

We use the following Luttinger parameters: $\gamma_1=4.14$, $\gamma_2=1.09$, $\gamma_3=1.62$, and $\gamma_{el}=10.42$ ($m_e = 0.096 m_0$) in the QW and in the barriers. A total discontinuity of bands $V_T=500$ meV and a valence band offset $vbo=0.4$ is assumed, meaning that the discontinuity of the valence band is $V_h=V_T \times vbo=200$ meV and the discontinuity of the conduction band is $V_{el}=V_T (1 - vbo)=300$ meV (see Fig. 1). We also choose a quantum well of $L_{QW}=20$ Å, for which the splitting between the heavy hole HH_1 and light hole LH_1 energy states is around 50 meV. Additionally, there is only one heavy hole state and one light hole state for these parameters.

We assume that the iron island is in a single domain state, with magnetization $\vec{M} = M_0 \vec{e}_x$ pointing in the x -direction (Fig. 1). We then calculate the non-homogeneous field $\vec{B}$ outside the micromagnet by solving the magnetostatic equations analytically. For instance, when the distance between the island and the QW is $d=10$ nm, the maximum value of the magnetic field is $|\vec{B}|_{max}=1$ T. On account of the large value of D_x , the local magnetic field $\vec{B}(\vec{r})$ can be thought of as a sum of two fields produced by magnetic charges localized on both poles. On each pole, the magnetic field is localized

in the x-direction. In the y-direction it extends over the whole width D_y . We also stress that the gradient of the magnetic field [17] is as large as 2 mT/Å for $d=10$ nm, so that a precise determination of $|\vec{B}|_{max}$ or magnetic field profile is not trivial even in such simple case of a single domain phase. In Fig. 2, we present the absorp-




FIG. 3: Absorption coefficient for different g_e -factors for a rectangular micromagnet. The ratio $|g_h/g_e|=4$ is assumed for the CdMnTe semiconductor quantum well structure; and we have chosen $d=10$ nm and $D_z=150$ nm.

tion spectrum at three distances d between the QW and the micromagnet: $d=10$ nm, $d=30$ nm, and $d=60$ nm. We have fixed the thickness of the micromagnet and the g -factors of the carriers. The numbers nm above each peak in Fig. 2 indicate transitions between the n th electron state and a m th hole state. Each transition line was broadened by a Gaussian function with a 1 meV width. In Fig. 1, as an example, the transition (11) is also shown as a dashed vertical line. At $d=10$ nm, the energy difference between the (11) peak and the MAE, which we call here binding energy, is around 66 meV. It should be noted that non-diagonal transitions, e.g. (24), are relatively strong in these hybrids, in contrast to a normal QW where only diagonal transitions such (11), (22), etc are strong. With increasing d the binding energy decreases as the local magnetic field - our "confining agent" - becomes smaller as the separation between the micromagnet and the QW increases.

In Fig. 3 we plot the absorption coefficient for different g_e -factors. The binding energy is a linearly increasing function of the g_e -factor for this range of g_e values. The effective g -factors are functions of temperature [6]. The top panel in Fig. 3 corresponds to a standard experi-

ment typically performed at a few Kelvins, whereas the bottom panel corresponds to a mili-Kelvin temperature measurement. As the thickness D_z of the micromagnet




FIG. 4: Absorption coefficient for different thickness D_z of a micromagnet. Distance between micromagnet and quantum well $d=10$ nm and $g_e=500$. Each transition energy is broadened by 1 meV (solid lines) and 4 meV (dashed lines).

increases (now d is constant), so does the binding energy, as can be seen in Fig. 4, where we present absorption coefficients for three thicknesses D_z . We can also relate this effect to the fact that the local magnetic field increases when we increase the thickness D_z of the island. This behavior persists as long as D_z is smaller than the in-plane dimensions. When $D_z \in (150, 300)$ Å, the binding energy is a linear function of D_z . As stated before, we use a line broadening of 1 meV in all the calculations. In order to show that our predictions are robust, we compare in Fig. 4 the 1 meV width absorption curve with another curve where the broadening line width is 4 meV. Even with such a large line width, the (11) peak is clearly visible. This is very promising and indicates that our predictions can be readily tested under typical experimental conditions.

In conclusion, we calculated the optical response of a hybrid structure composed of a rectangular micromagnet deposited on top of a diluted magnetic semiconductor quantum well structure. Our qualitative and quantitative analysis not only suggests the possibility localizing spin polarized states in this way, but also allows us to propose different routes for achieving this experimentally. In order to measure spin polarized objects inside the QW it is necessary to produce as large a local magnetic field as possible. This can be achieved, for example, by utilizing materials with high saturation magnetization. Our micromagnet simulations, together with the energy spectra analysis, show that it is better to deposit thicker ferromagnetic layers on top of the QW, as thicker micromagnets lead to an increased local magnetic field. As we expected, the growth of high quality QW relatively

close to the ferromagnetic/semiconductor interface is of great importance, as this enhances localization. Finally, since high values of g-factors are fundamental for the localization and the manufacturing of efficient traps, optical localization is expected to be observed at sub-Kelvin temperatures. Finally, since quasi one-dimensional states emerge only below the poles of the micromagnet, spa-

tially resolved techniques such as μ -PLE or NSOM are required to measure the effects presented in this paper.

This research was supported by the National Science Foundation under NSF-NIRT Grant No. DMR 02-10519, by the U.S. Department of Energy, Basic Energy Sciences, under Contract No. W-7405-ENG-36 and by the Alfred P. Sloan Foundation (B. J.).

-
- [1] I. Žutić, J. Fabian, and S. Das Sarma, *Rev. Mod. Phys.* **76**, 323 (2004).
 - [2] A. Wójs and P. Hawrylak, *Phys. Rev. B* **51**, 10880 (1995).
 - [3] P. Redliński and J. Kossut, *Semicond. Sci. and Technol.* **17**, 237 (2002).
 - [4] J. A. K. Freire, F. M. Peeters, A. Matulis, V. N. Freire, and G. A. Farias, *Phys. Rev. B* **62**, 7316 (2000).
 - [5] C. Riva, F. M. Peeters, and K. Varga, *Phys. Rev. B* **61**, 13873 (2000).
 - [6] J. A. Gaj, W. Grieshaber, C. Bodin-Deshayes, J. Cibert, G. Feuillet, Y. Merle d'Aubigne, and A. Wasiela, *Phys. Rev. B* **50**, 5512 (1994).
 - [7] J. K. Furdyna and J. Kossut, *Diluted Magnetic Semiconductor* (Academic, San Diego, 1988).
 - [8] J. D. Jackson, *Classical electrodynamics* (Wiley, New York, 1999), xxi ed.
 - [9] J. Kossut, I. Yamakawa, A. Nakamura, G. Cywiński, K. Fronc, M. Czczott, J. Wróbel, F. Kyrychenko, T. Wojtowicz, and S. Takeyama, *App. Phys. Lett.* **79**, 1789 (2001).
 - [10] G. Cywiński, M. Czczott, J. Wróbel, K. Fronc, A. Aleszkiewicz, S. Maćkowski, T. Wojtowicz, and J. Kossut, *Physica E* **13**, 560 (2002).
 - [11] P. A. Crowell, V. Nikitin, D. D. Awschalom, F. Flack, N. Samarth, and G. A. Prinz, *Journal of Applied Physics* **81**, 5441 (1997).
 - [12] M. J. Donahue and D. G. Porter, Interagency Report NISTIR 6376, National Institute of Standards and Technology (1999).
 - [13] T. Dietl, M. Sawicki, M. Dahl, D. Heiman, E. D. Isaacs, M. J. Graf, S. I. Gubarev, and D. L. Alov, *Phys. Rev. B* **43**, 3154 (1991).
 - [14] O. Madelung, *Introduction to Solid-State Theory* (Springer, New York, 1996), 3rd ed.
 - [15] J. M. Luttinger and W. Kohn, *Phys. Rev.* **97**, 969 (1955).
 - [16] M. Abolfath, T. Jungwirth, J. Brum, and A. H. MacDonald, *Phys. Rev. B* **63**, 054418 (2001).
 - [17] F. Pulizzi, P. C. M. Christianen, J. C. Maan, T. Wojtowicz, G. Karczewski, and J. Kossut, *Phys. Stat. Sol a* **178**, 33 (2000).